

A<sup>3</sup>.

2. (Amended) The dielectric substrates, as recited in claim 1, further comprising:  
said dielectric substrates being heated for at least 20 hours at between 1400° C and 1600 °

5 C;

said dielectric substrates having a low dielectric constant in the range of 4.1 to 16.3; and  
said dielectric substrates having a low dielectric loss in the range of less than  $1 \times 10^{-3}$  to  $9 \times 10^{-3}$  without a phase transition.

---

10

4. (Twice Amended) The dielectric substrate, according to claim 3, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite cubic crystalline structure;  
said dielectric substrate having a low dielectric constant of 15.1; and  
said dielectric substrate having a low dielectric loss of less than  $1 \times 10^{-3}$ .

---

15

7. (Twice Amended) The dielectric substrate, according to claim 6, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline  
structure;  
said dielectric substrate having a low dielectric constant of 5.1; and  
said dielectric substrate having a low dielectric loss of less than  $1.0 \times 10^{-3}$ .

---

20

10. (Twice Amended) The dielectric substrate, according to claim 9, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline  
structure;  
said dielectric substrate having a low dielectric constant of 10.0; and  
said dielectric substrate having a low dielectric loss of  $2.0 \times 10^{-3}$ .

---

30

13. (Twice Amended) The dielectric substrate, according to claim 12, further comprising:

B5  
5  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline structure;  
said dielectric substrate having a low dielectric constant of 5.3; and  
said dielectric substrate having a low dielectric loss of  $1.6 \times 10^{-3}$ .

---

B6  
10  
16. (Twice Amended) The dielectric substrate, according to claim 15, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline structure;  
said dielectric substrate having a low dielectric constant of 11.6; and  
said dielectric substrate having a low dielectric loss of about  $3.1 \times 10^{-3}$ .

---

15  
B7  
19. (Twice Amended) The dielectric substrate, according to claim 18, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline structure;  
said dielectric substrate having a low dielectric constant of 11.2; and  
said dielectric substrate having a low dielectric loss of less than  $1.0 \times 10^{-3}$ .

---

20  
B8  
22. (Twice Amended) The dielectric substrate, according to claim 21, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline structure;  
25  
said dielectric substrate having a low dielectric constant of 12.9; and  
said dielectric substrate having a low dielectric loss of  $1.4 \times 10^{-3}$ .

---

B9  
30  
25. (Twice Amended) The dielectric substrate, according to claim 24, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline

structure;

34  
said dielectric substrate having a low dielectric constant of 7.1; and  
said dielectric substrate having a low dielectric loss of  $1.4 \times 10^{-3}$ .

---

5  
30  
28. (Twice Amended) The dielectric substrate, according to claim 27, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite cubic crystalline structure;  
said dielectric substrate having a low dielectric constant of 16.3; and  
said dielectric substrate having a low dielectric loss of  $3.8 \times 10^{-3}$ .

---

10  
31. (Twice Amended) The dielectric substrate, according to claim 30, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline  
structure;  
15  
said dielectric substrate having a low dielectric constant of 12.1; and  
said dielectric substrate having a low dielectric loss of less than  $1.0 \times 10^{-3}$ .

---

20  
32  
34. (Twice Amended) The dielectric substrate, according to claim 33, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline  
structure;  
said dielectric substrate having a low dielectric constant of 13.6; and  
said dielectric substrate having a low dielectric loss of less than  $1.0 \times 10^{-3}$ .

---

25  
30  
33  
37. (Twice Amended) The dielectric substrate, according to claim 36, further comprising:  
said dielectric substrate is constructed in a bulk form;  
said dielectric substrate having an ordered perovskite pseudo-cubic tetragonal crystalline  
structure;  
said dielectric substrate having a low dielectric constant of 10.9; and  
said dielectric substrate having a low dielectric loss of  $2.2 \times 10^{-3}$ .